

English Version

## Aluminium and aluminium alloys - Extruded rod/bar, tube and profiles - Part 2: Mechanical properties

Aluminium et alliages d'aluminium - Barres, tubes et profilés filés - Partie 2: Caractéristiques mécaniques

Aluminium und Aluminiumlegierungen - Stranggepresste Stangen, Rohre und Profile - Teil 2: Mechanische Eigenschaften

This European Standard was approved by CEN on 10 February 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

<b>Contents</b>		Page
Foreword.....		3
<b>1</b>	<b>Scope .....</b>	<b>5</b>
<b>2</b>	<b>Normative references .....</b>	<b>5</b>
<b>3</b>	<b>Mechanical property limits .....</b>	<b>5</b>
<b>3.1</b>	<b>General.....</b>	<b>5</b>
<b>3.2</b>	<b>Elongation .....</b>	<b>5</b>
<b>3.3</b>	<b>Reference list of the tables of mechanical properties of the relevant aluminium and aluminium alloys.....</b>	<b>6</b>
<b>3.4</b>	<b>Tables of mechanical properties.....</b>	<b>8</b>
<b>Annex A (informative) List of tempers used in tables 1 to 57 (extract of EN 515).....</b>		<b>65</b>
<b>Bibliography .....</b>		<b>66</b>

## Foreword

This document (EN 755-2:2008) has been prepared by Technical Committee CEN/TC 132 "Aluminium and aluminium alloys", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2008, and conflicting national standards shall be withdrawn at the latest by September 2008.

This document supersedes EN 755-2:1997.

Within its programme of work, Technical committee CEN/TC 132 entrusted CEN/TC 132/WG 5 "*Extruded and drawn products*" to revise EN 755-2:1997.

The following technical modifications have been introduced during the revision:

- General: Typical Brinell hardness values are introduced in the tables for mechanical properties for information only  
The following new alloys are included; EN AW-3102, EN AW-5049, EN AW-6008, EN AW-6110A, EN AW-6014, EN AW-6023, EN AW-6360, EN AW-6262A and EN AW-6065, EN AW-6182, EN AW-7108, EN AW-7108A, EN AW-7021  
For Alloy EN AW-5005 and EN AW-5005A new temper H111 is added
- Subclause 3.2: A value should be used for elongation if not otherwise agreed, with exception of certain products
- Annex A: Informative Annex A added explaining temper designation used in all tables
- Former annexes A and B are deleted (content moved to Part 1)

EN 755 comprises the following parts under the general title "*Aluminium and aluminium alloys — Extruded rod/bar, tube and profiles*":

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Round bars, tolerances on dimensions and form*
- *Part 4: Square bars, tolerances on dimensions and form*
- *Part 5: Rectangular bars, tolerances on dimensions and form*
- *Part 6: Hexagonal bars, tolerances on dimensions and form*
- *Part 7: Seamless tubes, tolerances on dimensions and form*
- *Part 8: Porthole tubes, tolerances on dimensions and form*
- *Part 9: Profiles, tolerances on dimensions and form*

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

CEN/TC 132 affirms it is its policy that in the case when a patentee refuses to grant licenses on standardized standards products under reasonable and not discriminatory conditions then this product shall be removed from the corresponding standard.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## 1 Scope

This document specifies the mechanical property limits resulting from tensile testing applicable to aluminium and aluminium alloy extruded rod/bar, tube and profile.

Technical conditions for inspection and delivery, including product and testing requirements, are specified in EN 755-1. Temper designations are defined in EN 515. The chemical composition limits for these materials are given in EN 573-3.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references only the edition cited applies. For undated references the latest edition of the referenced document (including any amendments) applies.

EN 755-1, *Aluminium and aluminium alloys — Extruded rod/bar, tube and profiles — Part 1: Technical conditions for inspection and delivery*

EN 10002-1, *Metallic materials — Tensile testing — Part 1: Method of test at ambient temperature*

## 3 Mechanical property limits

### 3.1 General

The mechanical properties shall be in conformity with those specified in Tables 1 to 57 or those agreed upon between supplier and purchaser and stated in the order document.

Tables 1 to 57 contain limits of mechanical property values obtained by tensile testing according to EN 10002-1 after sampling and test piece preparation according to EN 755-1.

NOTE The mechanical properties refer to test pieces taken in the longitudinal direction. Mechanical properties of test pieces taken in other directions can differ from those for the longitudinal direction quoted in this standard.

Brinell hardness values given in Tables 1 to 57 expressed as *HBW* values are for information only.

### 3.2 Elongation

If not otherwise agreed, the *A* value shall be used.

The *A* value for elongation is the % elongation measured over a gauge length of  $5,65\sqrt{S_0}$  (where  $S_0$  is the initial cross-sectional area of the test-piece), and expressed in percent.

For certain products the supplier may choose (if not otherwise specified in the order documents) to use the elongation based on  $A_{50\text{mm}}$ . Consequently values for the  $A_{50\text{mm}}$  are included in the following tables.

The  $A_{50\text{mm}}$  value is the elongation measured over a gauge length of 50 mm and expressed in percent.

Test pieces and their location in the specimen are given in EN 755-1.

### 3.3 Reference list of the tables of mechanical properties of the relevant aluminium and aluminium alloys

			Page
Table 1	Aluminium EN AW-1050A	[Al 99,5]	8
Table 2	Aluminium EN AW-1070A	[Al 99,7]	9
Table 3	Aluminium EN AW-1200	[Al 99,0]	10
Table 4	Aluminium EN AW-1350	[EAl 99,5]	11
Table 5	Alloy EN AW-2007	[Al Cu <sub>4</sub> PbMgMn]	12
Table 6	Alloy EN AW-2011 and EN AW-2011A	[Al Cu <sub>6</sub> BiPb] and [Al Cu <sub>6</sub> BiPb(A)]	13
Table 7	Alloy EN AW-2014 and EN AW-2014A	[Al Cu <sub>4</sub> SiMg] and [Al Cu <sub>4</sub> SiMg(A)]	14
Table 8	Alloy EN AW-2017A	[Al Cu <sub>4</sub> MgSi(A)]	15
Table 9	Alloy EN AW-2024	[Al Cu <sub>4</sub> Mg1]	16
Table 10	Alloy EN AW-2030	[Al Cu <sub>4</sub> PbMg]	17
Table 11	Alloy EN AW-3102	[Al Mn <sub>0,2</sub> ]	18
Table 12	Alloy EN AW-3003	[Al Mn1Cu]	19
Table 13	Alloy EN AW-3103	[Al Mn1]	20
Table 14	Alloy EN AW-5005 and EN AW-5005A	[Al Mg1(B)] and [Al Mg 1(C)]	21
Table 15	Alloy EN AW-5019	[Al Mg5]	22
Table 16	Alloy EN AW-5049	[Al Mg <sub>2</sub> Mn <sub>0,8</sub> ]	23
Table 17	Alloy EN AW-5051A	[Al Mg <sub>2</sub> ]	24
Table 18	Alloy EN AW-5251	[Al Mg <sub>2</sub> Mn <sub>0,3</sub> ]	25
Table 19	Alloy EN AW-5052	[Al Mg <sub>2,5</sub> ]	26
Table 20	Alloy EN AW-5154A	[Al Mg <sub>3,5</sub> (A)]	27
Table 21	Alloy EN AW-5454	[Al Mg <sub>3</sub> Mn]	28
Table 22	Alloy EN AW-5754	[Al Mg <sub>3</sub> ]	29
Table 23	Alloy EN AW-5083	[Al Mg <sub>4,5</sub> Mn <sub>0,7</sub> ]	30
Table 24	Alloy EN AW-5086	[Al Mg <sub>4</sub> ]	31
Table 25	Alloy EN AW-6101A	[EAl MgSi(A)]	32
Table 26	Alloy EN AW-6101B	[EAl MgSi(B)]	33
Table 27	Alloy EN AW-6005 and EN AW-6005A	[Al SiMg] and [Al SiMg(A)]	34
Table 28	Alloy EN AW-6106	[Al MgSiMn]	35
Table 29	Alloy EN AW-6008	[Al SiMgV]	36
Table 30	Alloy EN AW-6110A	[Al Mg <sub>0,9</sub> Si <sub>0,9</sub> MnCu(A)]	37
Table 31	Alloy EN AW-6012	[Al MgSiPb]	38
Table 32	Alloy EN AW-6014	[Al Mg <sub>0,6</sub> SiV]	39
Table 33	Alloy EN AW-6018	[Al Mg <sub>1</sub> SiPbMn]	40
Table 34	Alloy EN AW-6023	[Al Si <sub>1</sub> Sn <sub>1</sub> MgBi]	41
Table 35	Alloy EN AW-6351	[Al Si <sub>1</sub> Mg <sub>0,5</sub> Mn]	42
Table 36	Alloy EN AW-6060	[Al MgSi]	43
Table 37	Alloy EN AW-6360	[Al SiMgMn]	44
Table 38	Alloy EN AW-6061	[Al Mg <sub>1</sub> SiCu]	45
Table 39	Alloy EN AW-6261	[Al Mg <sub>1</sub> SiCuMn]	46
Table 40	Alloy EN AW-6262	[Al Mg <sub>1</sub> SiPb]	47
Table 41	Alloy EN AW-6262A	[Al Mg <sub>1</sub> SiSn]	48
Table 42	Alloy EN AW-6063	[Al Mg <sub>0,7</sub> Si]	49
Table 43	Alloy EN AW-6063A	[Al Mg <sub>0,7</sub> Si(A)]	50
Table 44	Alloy EN AW-6463	[Al Mg <sub>0,7</sub> Si(B)]	51
Table 45	Alloy EN AW-6065	[Al Mg <sub>1</sub> Bi <sub>1</sub> Si]	52
Table 46	Alloy EN AW-6081	[Al Si <sub>0,9</sub> MgMn]	53
Table 47	Alloy EN AW-6082	[Al Si <sub>1</sub> MgMn]	54
Table 48	Alloy EN AW-6182	[Al Si <sub>1</sub> MgZr]	55
Table 49	Alloy EN AW-7003	[Al Zn <sub>6</sub> Mg <sub>0,8</sub> Zr]	56

Table 50	Alloy EN AW-7005	[Al Zn4,5Mg1,5Mn]	57
Table 51	Alloy EN-AW-7108	[Al Zn5Mg1Zr]	58
Table 52	Alloy EN-AW- 7108A	[Al Zn5Mg1Zr(A)]	59
Table 53	Alloy EN AW-7020	[Al Zn4,5Mg1]	60
Table 54	Alloy EN AW-7021	[Al Zn5,5Mg1,5]	61
Table 55	Alloy EN AW-7022	[Al Zn5Mg3Cu]	62
Table 56	Alloy EN AW-7049A	[Al Zn8MgCu]	63
Table 57	Alloy EN AW-7075	[Al Zn5,5MgCu]	64

### 3.4 Tables of mechanical properties

Table 1 — Aluminium EN AW-1050A [Al 99,5]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	60	-	20	-	25	23	20
O, H111	all	all	60	95	20	-	25	23	20
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	60		20	-	25	23	20	
O, H111	all	60	95	20	-	25	23	20	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	60		20	-	25	23	20	

<sup>a</sup>  $D$  = Diameter for round bar.

<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.

<sup>c</sup> F Temper: property values are for information only.



Table 2 — Aluminium EN AW-1070A [Al 99,7]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	60	-	23		25	23	18
Extruded tube Not specified									
Extruded profile Not specified									
<p><sup>a</sup> <math>D</math> = Diameter for round bar.</p> <p><sup>b</sup> <math>S</math> = Width across flats for square and hexagonal bar, thickness for rectangular bar.</p> <p><sup>c</sup> F Temper: property values are for information only.</p>									

Table 3 — Aluminium EN AW-1200 [Al 99,0]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	75	-	25	-	20	18	23
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	75	-	25		20	18	23
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all		75	-	25		20	18	23
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> F Temper: property values are for information only.									

Table 4 — Aluminium EN AW-1350 [EAI 99,5]

Extruded rod/bar <sup>d</sup>									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	60	-	-	-	25	23	20
Extruded tube <sup>d</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	60	-	-	-	25	23	20
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all		60	-	-	-	25	23	20
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> F Temper: property values are for information only. <sup>d</sup> Electrical conductivity $\gamma \geq 35,4$ MS/m.									

Table 5 — Alloy EN AW-2007 [Al Cu4PbMgMn]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 <sup>c</sup>	$\leq 80$	$\leq 80$	370	-	250	-	8	6	95
	$80 < D \leq 200$	$80 < S \leq 200$	340	-	220	-	8	-	
	$200 < D \leq 250$	$200 < S \leq 250$	330	-	210	-	7	-	
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 <sup>c</sup>	$\leq 25$		370	-	250	-	8	6	95
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 <sup>c</sup>	$\leq 30$		370	-	250	-	8	6	95
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 6 — Alloy EN AW-2011 [Al Cu6BiPb] and Alloy EN AW-2011A [Al Cu6BiPb(A)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T4 <sup>c</sup>	≤ 200	≤ 60	275	-	125	-	14	12	95
T6 <sup>c</sup>	≤ 75	≤ 60	310	-	230	-	8	6	110
	75 < $D$ ≤ 200	-	295	-	195	-	6	-	110
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 25		310	-	230	-	6	4	110
Extruded profile Not specified									
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 7 — Alloy EN AW-2014 [Al Cu4SiMg] and Alloy EN AW-2014A [Al Cu4SiMg(A)]

Drawn rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	250	-	135	12	10	45
T4, T4510, T4511	≤ 25	≤ 25	370	-	230	-	13	11	110
	25 < $D$ ≤ 75	25 < $S$ ≤ 75	410	-	270	-	12	-	110
	75 < $D$ ≤ 150	75 < $S$ ≤ 150	390	-	250	-	10	-	110
	150 < $D$ ≤ 200	150 < $S$ ≤ 200	350	-	230	-	8	-	110
T6, T6510, T6511	≤ 25	≤ 25	415	-	370	-	6	5	140
	25 < $D$ ≤ 75	25 < $S$ ≤ 75	460	-	415	-	7	-	140
	75 < $D$ ≤ 150	75 < $S$ ≤ 150	465	-	420	-	7	-	140
	150 < $D$ ≤ 200	150 < $S$ ≤ 200	430	-	350	-	6	-	140
	200 < $D$ ≤ 250	200 < $S$ ≤ 250	420	-	320	-	5	-	140
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	≤ 20		-	250	-	135	12	10	45
T4, T4510, T4511	≤ 20		370	-	230	-	11	10	110
T6, T6510, T6511	≤ 10		415	-	370	-	7	5	140
	10 < $t$ ≤ 40		450	-	400	-	6	4	140
Extruded profile <sup>c</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	all		-	250	-	135	12	10	45
T4, T4510, T4511	≤ 25		370	-	230	-	11	10	110
	25 < $t$ ≤ 75		410	-	270	-	10	-	110
T6, T6510, T6511	≤ 25		415	-	370	-	7	5	140
	25 < $D$ ≤ 75		460	-	415	-	7	-	140

<sup>a</sup>  $D$  = Diameter for round bar.

<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.

<sup>c</sup> If a profile cross section is comprised of different thicknesses which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.

Table 8 — Alloy EN AW-2017A [Al Cu4MgSi(A)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0.2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	$\leq 200$	$\leq 200$	-	250	-	135	12	10	45
T4, T4510, T4511 <sup>c</sup>	$\leq 25$	$\leq 25$	380	-	260	-	12	10	105
	$25 < D \leq 75$	$25 < S \leq 75$	400	-	270	-	10	-	105
	$75 < D \leq 150$	$75 < S \leq 150$	390	-	260	-	9	-	105
	$150 < D \leq 200$	$150 < S \leq 200$	370	-	240	-	8	-	105
	$200 < D \leq 250$	$200 < S \leq 250$	360	-	220	-	7	-	105
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0.2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	$\leq 20$		-	250	-	135	12	10	45
T4, T4510, T4511 <sup>c</sup>	$\leq 10$		380	-	260	-	12	10	105
	$10 < t \leq 75$		400	-	270	-	10	8	105
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0.2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 <sup>c</sup>	$\leq 30$		380	-	260	-	10	8	105
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 9 — Alloy EN AW-2024 [AL Cu4Mg1]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	250	-	150	12	10	47
T3, T3510, T3511	≤ 50	≤ 50	450	-	310	-	8	6	120
	50 < $D$ ≤ 100	50 < $S$ ≤ 100	440	-	300	-	8	-	120
	100 < $D$ ≤ 200	100 < $S$ ≤ 200	420	-	280	-	8	-	120
	200 < $D$ ≤ 250	200 < $S$ ≤ 250	400	-	270	-	8	-	120
T8, T8510, T8511	≤ 150	≤ 150	455	-	380	-	5	4	130
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	≤ 30		-	250	-	150	12	10	47
T3, T3510, T3511	≤ 30		420	-	290	-	8	6	120
T8, T8510, T8511	≤ 30		455	-	380	-	5	4	130
Extruded profile <sup>c</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	all		-	250	-	150	12	10	47
T3, T3510, T3511	≤ 15		395	-	290	-	8	6	120
	15 < $t$ ≤ 50		420	-	290	-	8	-	120
T8, T8510, T8511	≤ 50		455	-	380	-	5	4	130
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									



Table 10 — Alloy EN AW-2030 [Al Cu4PbMg]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 <sup>c</sup>	$\leq 80$	$\leq 80$	370	-	250	-	8	6	115
	$80 < D \leq 200$	$80 < S \leq 200$	340	-	220	-	8	-	115
	$200 < D \leq 250$	$200 < S \leq 250$	330	-	210	-	7	-	115
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 <sup>c</sup>	$\leq 25$		370	-	250	-	8	6	115
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T4, T4510, T4511 <sup>c</sup>	$\leq 30$		370	-	250	-	8	6	115
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 11 — Alloy EN AW-3102 [Al Mn0,2]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	80	-	30	-	25	23	23
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	80	-	30	-	25	23	23	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	80	-	30	-	25	23	23	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> F Temper: property values are for information only.									

Table 12 — Alloy EN AW-3003 [Al Mn1Cu]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.			
F <sup>c</sup> , H112	all	all	95	-	35	-	25	20	30
O, H111	all	all	95	135	35	-	25	20	30
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
F <sup>c</sup> , H112	all	95	-	35	-	25	20	30	
O, H111	all	95	135	35	-	25	20	30	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
F <sup>c</sup> , H112	all	95	-	35	-	25	20	30	

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> F Temper: property values are for information only.

Table 13 — Alloy EN AW-3103 [Al Mn1]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.			
F <sup>c</sup> , H112	all	all	95	-	35	-	25	20	28
O, H111	all	all	95	135	35	-	25	20	28
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
F <sup>c</sup> , H112	all	95	-	35	-	25	20	28	
O, H111	all	95	135	35	-	25	20	28	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
F <sup>c</sup> , H112	all	95	-	35	-	25	20	28	

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> F Temper: property values are for information only.

Table 14 — Alloy EN AW-5005 [Al Mg1(B)] and Alloy EN AW-5005A [Al Mg1(C)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	100	100	-	40	-	18	16	30
O, H111	≤ 80	≤ 60	100	150	40	-	18	16	30
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	100	-	40	-	18	16	30	
O, H111	≤ 20	100	150	40	-	20	18	30	
Extruded Profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	100	-	40	-	18	16	30	
O, H111	≤ 20	100	150	40	-	20	18	30	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> F Temper: property values are for information only.									

Table 15 — Alloy EN AW-5019 [Al Mg5]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	≤ 200	≤ 200	250	-	110	-	14	12	65
O, H111	≤ 200	≤ 200	250	320	110	-	15	13	65
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	≤ 30		250	-	110	-	14	12	65
O, H111	≤ 30		250	320	110	-	15	13	65
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	≤ 30		250	-	110	-	14	12	65

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> F Temper: property values are for information only.

Table 16 — Alloy EN AW-5049 [Al Mg2Mn0,8]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	180	-	80	-	15	13	50
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	180	-	80	-	15	13	50	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	180	-	80	-	15	13	50	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> F Temper: property values are for information only.									

Table 17 — Alloy EN AW-5051A [Al Mg2]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	150	-	50	-	16	14	40
O, H111	all	all	150	200	50	-	18	16	40
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	150	-	60	-	16	14	40	
O, H111	all	150	200	60	-	18	16	40	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	150	-	60	-	16	14	40	

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> F Temper: property values are for information only.



Table 18 — Alloy EN AW-5251 [Al Mg2Mn0,3]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	160	-	60	-	16	14	45
O, H111	all	all	160	220	60	-	17	15	45
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	160	-	60	-	16	14	45	
O, H111	all	160	220	60	-	17	15	45	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	160	-	60	-	16	14	45	

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> F Temper: property values are for information only.

Table 19 — Alloy EN AW-5052 [Al Mg2,5]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	all	all	170	-	70	-	15	13	47
O, H111	all	all	170	230	70	-	17	15	45
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	170	-	70	-	15	13	47	
O, H111	all	170	230	70	-	17	15	45	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	170	-	70	-	15	13	47	

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> F Temper: property values are for information only.

Table 20 — Alloy EN AW-5154A [Al Mg3,5(A)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	≤ 200	≤ 200	200	-	85	-	16	14	55
O, H111	≤ 200	≤ 200	200	275	85	-	18	16	55
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	≤ 25	200	-	85	-	16	14	55	
O, H111	≤ 25	200	275	85	-	18	16	55	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	≤ 25	200	-	85	-	16	14	55	

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> F Temper: property values are for information only.

Table 21 — Alloy EN AW-5454 [Al Mg3Mn]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.			
F <sup>c</sup> , H112	≤ 200	≤ 200	200	-	85	-	16	14	60
O, H111	≤ 200	≤ 200	200	275	85	-	18	16	60
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
F <sup>c</sup> , H112	≤ 25	200	-	85	-	16	14	60	
O, H111	≤ 25	200	275	85	-	18	16	60	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
F <sup>c</sup> , H112	≤ 25	200	-	85	-	16	14	60	

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> F Temper: property values are for information only.

Table 22 — Alloy EN AW-5754 [Al Mg3]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	≤ 150	≤ 150	180	-	80	-	14	12	47
	150 < $D$ ≤ 250	200 < $S$ ≤ 250	180	-	70	-	13	-	47
O, H111	≤ 150	≤ 150	180	250	80	-	17	15	45
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	≤ 25		180	-	80	-	14	12	47
O, H111	≤ 25		180	250	80	-	17	15	45
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	≤ 25		180	-	80	-	14	12	47
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> F Temper: property values are for information only.									

Table 23 — Alloy EN AW-5083 [Al Mg4,5Mn0,7]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup>	≤ 200	≤ 200	270	-	110	-	12	10	70
	200 < $D$ ≤ 250	200 < $S$ ≤ 250	260	-	100	-	12	-	70
O, H111	≤ 200	≤ 200	270	-	110	-	12	10	70
H112	≤ 200	≤ 200	270	-	125	-	12	10	70
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
F <sup>c</sup>	all		270	-	110	-	12	10	70
O, H111	all		270	-	110	-	12	10	70
H112	all		270	-	125	-	12	10	70
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
F <sup>c</sup>	all		270	-	110	-	12	10	70
H112	all		270	-	125	-	12	10	70

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> F Temper: property values are for information only.

Table 24 — Alloy EN AW-5086 [Al Mg4]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
F <sup>c</sup> , H112	≤ 250	≤ 250	240	-	95	-	12	10	65
O, H111	≤ 200	≤ 200	240	320	95	-	18	15	65
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	240	-	95	-	12	10	65	
O, H111	all	240	320	95	-	18	15	65	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
F <sup>c</sup> , H112	all	240	-	95	-	12	10	65	

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> F Temper: property values are for information only.

Table 25 — Alloy EN AW-6101A [EAI MgSi(A)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 150	≤ 150	200	-	170	-	10	8	70
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T6 <sup>c</sup>	≤ 25	200	-	170	-	10	8	70	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T6 <sup>c</sup>	≤ 50	200	-	170	-	10	8	70	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									



Table 26 — Alloy EN AW-6101B [EAI MgSi(B)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6 <sup>cd</sup>	-	≤ 15	215	-	160	-	8	6	70
T7 <sup>ce</sup>	-	≤ 15	170	-	120	-	12	10	60
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>cd</sup>	≤ 15		215	-	160	-	8	6	70
T7 <sup>ce</sup>	≤ 15		170	-	120	-	12	10	60
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>cd</sup>	≤ 15		215	-	160	-	8	6	70
T7 <sup>ce</sup>	≤ 15		170	-	120	-	12	10	60
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching. <sup>d</sup> Electrical conductivity $\gamma \geq 30$ MS/m. <sup>e</sup> Electrical conductivity $\gamma \geq 32$ MS/m.									

Table 27 — Alloy EN AW-6005 [Al SiMg] and Alloy EN AW-6005A [Al SiMg(A)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	$\leq 25$	$\leq 25$	270	-	225	-	10	8	90
	$25 < D \leq 50$	$25 < S \leq 50$	270	-	225	-	8	-	90
	$50 < D \leq 100$	$50 < S \leq 100$	260	-	215	-	8	-	85
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	$\leq 5$		270	-	225	-	8	6	90
	$5 < t \leq 10$		260	-	215	-	8	6	85
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
<i>Open profile</i> T4 <sup>c</sup>	$\leq 25$		180	-	90	-	15	13	50
<i>Open profile</i> T6 <sup>c</sup>	$\leq 5$		270	-	225	-	8	6	90
	$5 < t \leq 10$		260	-	215	-	8	6	85
	$10 < t \leq 25$		250	-	200	-	8	6	85
<i>Hollow profile</i> T4 <sup>c</sup>	$\leq 10$		180	-	90	-	15	13	50
<i>Hollow profile</i> T6 <sup>c</sup>	$\leq 5$		255	-	215	-	8	6	85
	$5 < t \leq 15$		250	-	200	-	8	6	85
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching. <sup>d</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 28 — Alloy EN AW-6106 [Al MgSiMn]

Extruded rod/bar Not specified								
Extruded tube Not specified								
Extruded profile								
Temper	Wall thickness <i>t</i> mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
		min.	max.	min.	max.	min.	min.	
T6 <sup>a</sup>	≤ 10	250	-	200	-	8	6	75
<sup>a</sup> Properties may be obtained by press quenching.								

BS EN 755-2:2008

Table 29 — Alloy EN AW-6008 [Al SiMgV]

Extruded rod/bar Not specified								
Extruded tube								
Temper	Wall thickness <i>t</i> mm	<i>R<sub>m</sub></i> MPa		<i>R<sub>p0,2</sub></i> MPa		<i>A</i> % min.	<i>A</i> <sub>50 mm</sub> % min.	<i>HBW</i> Typical value
		min.	max.	min.	max.			
T4	≤ 10	180	-	90		15	13	50
T6 <sup>a</sup>	≤ 5	270	-	225	-	8	6	90
	5 < <i>t</i> ≤ 10	260	-	215	-	8	6	85
Extruded profile <sup>b</sup>								
Temper	Wall thickness <i>t</i> mm	<i>R<sub>m</sub></i> MPa		<i>R<sub>p0,2</sub></i> MPa		<i>A</i> % min.	<i>A</i> <sub>50 mm</sub> % min.	<i>HBW</i> Typical value
		min.	max.	min.	max.			
<i>Open profile</i> T4 <sup>a</sup>	≤ 10	180	-	90	-	15	13	50
<i>Open profile</i> T6 <sup>a</sup>	≤ 5	270	-	225	-	8	6	90
	5 < <i>t</i> ≤ 10	260	-	215	-	8	6	85
<i>Hollow profile</i> T4 <sup>a</sup>	≤ 10	180	-	90	-	15	13	50
<i>Hollow profile</i> T6 <sup>a</sup>	≤ 5	255	-	215	-	8	6	85
	5 < <i>t</i> ≤ 10	250	-	200	-	8	6	85
<sup>a</sup> Properties may be obtained by press quenching.								
<sup>b</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.								

Table 30 — Alloy EN AW-6110A [Al Mg<sub>0,9</sub>Si<sub>0,9</sub>MnCu(A)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.			
T5 <sup>c</sup>	≤ 120	≤ 120	380	-	360	-	10	8	115
T6 <sup>c</sup>	≤ 120	≤ 150	410	-	380	-	10	8	120
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
T4 <sup>c</sup>	≤ 25	320	-	220	-	16	14	85	
T6 <sup>c</sup>	≤ 25	380	-	360	-	10	8	120	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
T4 <sup>c</sup>	≤ 25	320	-	220	-	16	14	85	
T6 <sup>c</sup>	≤ 25	380	-	360	-	10	8	120	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 31 — Alloy EN AW-6012 [Al MgSiPb]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 <sup>c</sup>	$\leq 150$	$\leq 150$	310	-	260	-	8	6	105
	$150 < D \leq 200$	$150 < S \leq 200$	260	-	200	-	8	-	105
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 <sup>c</sup>	$\leq 30$		310	-	260	-	8	6	105
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 <sup>c</sup>	$\leq 30$		310	-	260	-	8	6	105
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 32 — Alloy EN AW-6014 [Al Mg0,6SiV]

Extruded rod/bar Not specified								
Extruded tube								
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
		min.	max.	min.	max.	min.	min.	
T4 <sup>a</sup>	≤ 10	140	-	70	-	15	13	55
T6 <sup>a</sup>	≤ 5	250	-	200	-	8	6	80
	5 < $t$ ≤ 10	225	-	180	-	8	6	80
Extruded profile <sup>b</sup>								
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
		min.	max.	min.	max.	min.	min.	
<i>Open profile</i> T4 <sup>a</sup>	≤ 10	140	-	70	-	15	13	55
<i>Open profile</i> T6 <sup>a</sup>	≤ 5	250	-	200	-	10	8	80
	5 < $t$ ≤ 10	225	-	180	-	8	6	80
<i>Hollow profile</i> T4 <sup>a</sup>	≤ 10	140	-	70	-	15	13	55
<i>Hollow profile</i> T6 <sup>a</sup>	≤ 5	250	-	200	-	8	6	80
	5 < $t$ ≤ 10	225	-	180	-	8	6	80
<sup>a</sup> Properties may be obtained by press quenching. <sup>b</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.								

Table 33 — Alloy EN AW-6018 [Al Mg1SiPbMn]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 <sup>c</sup>	$\leq 150$	$\leq 150$	310	-	260	-	8	6	-
	$150 < D \leq 200$	$150 < S \leq 200$	260	-	200	-	8	-	-
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 <sup>c</sup>	$\leq 30$		310	-	260	-	8	6	-
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 <sup>c</sup>	$\leq 30$		310	-	260	-	8	6	-
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									



Table 34 — Alloy EN AW-6023 [Al Si1Sn1MgBi]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 <sup>c</sup>	≤ 150	≤ 150	320	-	270	-	10	8	-
Extruded tube Not specified									
Extruded profile Not specified									
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 35 — Alloy EN AW-6351 [Al Si1Mg0,5Mn]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	160	-	110	14	12	35
T4 <sup>c</sup>	≤ 200	≤ 200	205	-	110	-	14	12	67
T6 <sup>c</sup>	≤ 20	≤ 20	295	-	250	-	8	6	95
	20 < $D$ ≤ 75	20 < $S$ ≤ 75	300	-	255	-	8	-	95
	75 < $D$ ≤ 150	75 < $S$ ≤ 150	310	-	260	-	8	-	95
	150 < $D$ ≤ 200	150 < $S$ ≤ 200	280	-	240	-	6	-	95
	200 < $D$ ≤ 250	200 < $S$ ≤ 250	270	-	200	-	6	-	95
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	≤ 25		-	160	-	110	14	12	35
T4 <sup>c</sup>	≤ 25		205	-	110	-	14	12	67
T6 <sup>c</sup>	≤ 5		290	-	250	-	8	6	95
	5 < $t$ ≤ 25		300	-	255	-	10	8	95
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	all		-	160	-	110	14	12	35
T4 <sup>c</sup>	≤ 25		205	-	110	-	14	12	67
Open profile T5	≤ 5		270	-	230	-	8	6	90
Open profile T6 <sup>c</sup>	≤ 5		290	-	250	-	8	6	95
	5 < $t$ ≤ 25		300	-	255	-	10	8	95
Hollow profile T5	≤ 5		270	-	230	-	8	6	90
Hollow profile T6 <sup>c</sup>	≤ 5		290	-	250	-	8	6	95
	5 < $t$ ≤ 25		300	-	255	-	10	8	95

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> Properties may be obtained by press quenching.  
<sup>d</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.

Table 36 — Alloy EN AW-6060 [Al MgSi]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T4 <sup>c</sup>	≤ 150	≤ 150	120	-	60	-	16	14	50
T5	≤ 150	≤ 150	160	-	120	-	8	6	60
T6 <sup>c</sup>	≤ 150	≤ 150	190	-	150	-	8	6	70
T64 <sup>cd</sup>	≤ 50	≤ 50	180	-	120	-	12	10	60
T66 <sup>c</sup>	≤ 150	≤ 150	215	-	160	-	8	6	75
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T4 <sup>c</sup>	≤ 15	120	-	60	-	16	14	50	
T5	≤ 15	160	-	120	-	8	6	60	
T6 <sup>c</sup>	≤ 15	190	-	150	-	8	6	70	
T64 <sup>cd</sup>	≤ 15	180	-	120	-	12	10	60	
T66 <sup>c</sup>	≤ 15	215	-	160	-	8	6	75	
Extruded profile <sup>e</sup>									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T4 <sup>c</sup>	≤ 25	120	-	60	-	16	14	50	
T5	≤ 5	160	-	120	-	8	6	60	
	5 < $t$ ≤ 25	140	-	100	-	8	6	60	
T6 <sup>c</sup>	≤ 3	190	-	150	-	8	6	70	
	3 < $t$ ≤ 25	170	-	140	-	8	6	70	
T64 <sup>cd</sup>	≤ 15	180	-	120	-	12	10	60	
T66 <sup>c</sup>	≤ 3	215	-	160	-	8	6	75	
	3 < $t$ ≤ 25	195	-	150	-	8	6	75	

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> Properties may be obtained by press quenching.  
<sup>d</sup> Bending quality.  
<sup>e</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.

Table 37 — Alloy EN AW-6360 [Al SiMgMn]

Extruded rod/bar									
Temper	Dimensions Mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T4 <sup>c</sup>	≤ 150	≤ 150	110	-	50	-	16	14	40
T5	≤ 150	≤ 150	150	-	110	-	8	6	50
T6 <sup>c</sup>	≤ 150	≤ 150	185	-	140	-	8	6	60
T66 <sup>c</sup>	≤ 150	≤ 150	195	-	150	-	8	6	65
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T4 <sup>c</sup>	≤ 15	110	-	50	-	16	14	40	
T5	≤ 15	150	-	120	-	8	6	50	
T6 <sup>c</sup>	≤ 15	185	-	140	-	8	6	60	
T66 <sup>c</sup>	≤ 15	195	-	150	-	8	6	65	
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T4 <sup>c</sup>	≤ 25	110	-	50	-	16	14	40	
T5	≤ 25	150	-	110	-	8	6	50	
T6 <sup>c</sup>	≤ 25	185	-	140	-	8	6	60	
T66 <sup>c</sup>	≤ 25	195	-	150	-	8	6	65	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching. <sup>d</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 38 — Alloy EN AW-6061 [Al Mg1SiCu]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	150	-	110	16	14	30
T4 <sup>c</sup>	≤ 200	≤ 200	180	-	110	-	15	13	65
T6 <sup>c</sup>	≤ 200	≤ 200	260	-	240	-	8	6	95
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
O, H111	≤ 25	-	150	-	110	16	14	30	
T4 <sup>c</sup>	≤ 25	180	-	110	-	15	13	65	
T6 <sup>c</sup>	≤ 5	260	-	240	-	8	6	95	
	5 < $t$ ≤ 25	260	-	240	-	10	8	95	
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T4 <sup>c</sup>	≤ 25	180	-	110	-	15	13	65	
T6 <sup>c</sup>	≤ 5	260	-	240	-	9	7	95	
	5 < $t$ ≤ 25	260	-	240	-	10	8	95	

<sup>a</sup>  $D$  = Diameter for round bar.

<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.

<sup>c</sup> Properties may be obtained by press quenching.

<sup>d</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.

Table 39 — Alloy EN AW-6261 [Al Mg1SiCuMn]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	≤ 100	≤ 100	-	170	-	120	14	12	-
T4 <sup>c</sup>	≤ 100	≤ 100	180	-	100	-	14	12	-
T6 <sup>c</sup>	≤ 20	≤ 20	290	-	245	-	8	7	100
	20 < $D$ ≤ 100	20 < $S$ ≤ 100	290	-	245	-	8	-	100
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	≤ 10		-	170	-	120	14	12	-
T4 <sup>c</sup>	≤ 10		180	-	100	-	14	12	-
T5	≤ 5		270	-	230	-	8	7	-
	5 < $t$ ≤ 10		260	-	220	-	9	8	-
T6 <sup>c</sup>	≤ 5		290	-	245	-	8	7	100
	5 < $t$ ≤ 10		290	-	245	-	9	8	100
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	all		-	170	-	120	14	12	-
T4 <sup>c</sup>	≤ 25		180	-	100	-	14	12	-
Open profile T5	≤ 5		270	-	230	-	8	7	-
	5 < $t$ ≤ 25		260	-	220	-	9	8	-
	> 25		250	-	210	-	9	-	-
Open profile T6 <sup>c</sup>	≤ 5		290	-	245	-	8	7	100
	5 < $t$ ≤ 25		280	-	235	-	8	7	100
Hollow profile T5	≤ 5		270	-	230	-	8	7	-
	5 < $t$ ≤ 10		260	-	220	-	9	8	-
Hollow profile T6 <sup>c</sup>	≤ 5		290	-	245	-	8	7	100
	5 < $t$ ≤ 10		270	-	230	-	9	8	100

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> Properties may be obtained by press quenching.  
<sup>d</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.

Table 40 — Alloy EN AW-6262 [Al Mg1SiPb]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.			
T6 <sup>c</sup>	≤ 200	≤ 200	260	-	240	-	10	8	75
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
T6 <sup>c</sup>	≤ 25	260	-	240	-	10	8	75	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
T6 <sup>c</sup>	≤ 25	260	-	240	-	10	8	75	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 41 — Alloy EN AW-6262A [Al Mg1SiSn]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 220	≤ 155	260	-	240	-	10	8	-
Extruded tube Not specified									
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T6 <sup>c</sup>	≤ 25	260	-	240	-	10	8	-	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									



Table 42 — Alloy EN AW-6063 [Al Mg0,7Si]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	130	-	-	18	16	25
T4 <sup>c</sup>	≤ 150	≤ 150	130	-	65	-	14	12	50
	150 < $D$ ≤ 200	150 < $S$ ≤ 200	120	-	65	-	12	-	50
T5	≤ 200	≤ 200	175	-	130	-	8	6	65
T6 <sup>c</sup>	≤ 150	≤ 150	215	-	170	-	10	8	75
	150 < $D$ ≤ 200	150 < $S$ ≤ 200	195	-	160	-	10	-	75
T66 <sup>c</sup>	≤ 200	≤ 200	245	-	200	-	10	8	80
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	≤ 25		-	130	-	-	18	16	25
T4 <sup>c</sup>	≤ 10		130	-	65	-	14	12	50
	10 < $t$ ≤ 25		120	-	65	-	12	10	50
T5	≤ 25		175	-	130	-	8	6	65
T6 <sup>c</sup>	≤ 25		215	-	170	-	10	8	75
T66 <sup>c</sup>	≤ 25		245	-	200	-	10	8	80
Extruded profile <sup>e</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T4 <sup>c</sup>	≤ 25		130	-	65	-	14	12	50
T5	≤ 3		175	-	130	-	8	6	65
	3 < $t$ ≤ 25		160	-	110	-	7	5	65
T6 <sup>c</sup>	≤ 10		215	-	170	-	8	6	75
	10 < $t$ ≤ 25		195	-	160	-	8	6	75
T64 <sup>c,d</sup>	≤ 15		180	-	120	-	12	10	65
T66 <sup>c</sup>	≤ 10		245	-	200	-	8	6	80
	10 < $t$ ≤ 25		225	-	180	-	8	6	80

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> Properties may be obtained by press quenching.  
<sup>d</sup> Bending quality.  
<sup>e</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.

Table 43 — Alloy EN AW-6063A [Al Mg0,7Si(A)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	$\leq 200$	$\leq 200$	-	150	-	-	16	14	28
T4 <sup>c</sup>	$\leq 150$	$\leq 150$	150	-	90	-	12	10	50
	$150 < D \leq 200$	$150 < S \leq 200$	140	-	90	-	10	-	50
T5	$\leq 200$	$\leq 200$	200	-	160	-	7	5	75
T6 <sup>c</sup>	$\leq 150$	$\leq 150$	230	-	190	-	7	5	80
	$150 < D \leq 200$	$150 < S \leq 200$	220	-	160	-	7	-	80
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	$\leq 25$		-	150	-	-	16	14	28
T4 <sup>c</sup>	$\leq 10$		150	-	90	-	12	10	50
	$10 < t \leq 25$		140	-	90	-	10	8	50
T5	$\leq 25$		200	-	160	-	7	5	75
T6 <sup>c</sup>	$\leq 25$		230	-	190	-	7	5	80
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T4 <sup>c</sup>	$\leq 25$		150	-	90	-	12	10	50
T5	$\leq 10$		200	-	160	-	7	5	75
	$10 < t \leq 25$		190	-	150	-	6	4	75
T6 <sup>c</sup>	$\leq 10$		230	-	190	-	7	5	80
	$10 < t \leq 25$		220	-	180	-	5	4	80
<p><sup>a</sup> <math>D</math> = Diameter for round bar.</p> <p><sup>b</sup> <math>S</math> = Width across flats for square and hexagonal bar, thickness for rectangular bar.</p> <p><sup>c</sup> Properties may be obtained by press quenching.</p> <p><sup>d</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.</p>									

Table 44 — Alloy EN AW-6463 [Al Mg0,7Si(B)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.			
T4 <sup>c</sup>	≤ 150	≤ 150	125	-	75	-	14	12	46
T5	≤ 150	≤ 150	150	-	110	-	8	6	60
T6 <sup>c</sup>	≤ 150	≤ 150	195	-	160	-	10	8	74
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value
	min.	max.	min.	max.					
T6 <sup>c</sup>	≤ 25		195	-	160	-	10	8	74
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value
	min.	max.	min.	max.					
T4 <sup>c</sup>	≤ 50		125	-	75	-	14	12	46
T5	≤ 50		150	-	110	-	8	6	60
T6 <sup>c</sup>	≤ 50		195	-	160	-	10	8	74
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching. <sup>d</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									

Table 45 — Alloy EN AW-6065 [Al Mg1SiBi1]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 220	≤ 155	260	-	240	-	10	8	-
Extruded tube Not specified									
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 25		260	-	240	-	10	8	-
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 46 — Alloy EN AW-6081 [Al Si0,9MgMn]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 250	≤ 250	275	-	240	-	8	6	95
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T6 <sup>c</sup>	≤ 25	275	-	240	-	8	6	95	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
<i>Open profile</i> T6 <sup>c</sup>	≤ 25	275	-	240	-	8	6	95	
<i>Hollow profile</i> T6 <sup>c</sup>	≤ 15	275	-	240	-	8	6	95	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 47 — Alloy EN AW-6082 [Al Si1MgMn]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	160	-	110	14	12	35
T4 <sup>c</sup>	≤ 200	≤ 200	205	-	110	-	14	12	70
T6 <sup>c</sup>	≤ 20	≤ 20	295	-	250	-	8	6	95
	20 < $D$ ≤ 150	20 < $S$ ≤ 150	310	-	260	-	8	-	95
	150 < $D$ ≤ 200	150 < $S$ ≤ 200	280	-	240	-	6	-	95
	200 < $D$ ≤ 250	200 < $S$ ≤ 250	270	-	200	-	6	-	95
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	≤ 25		-	160	-	110	14	12	35
T4 <sup>c</sup>	≤ 25		205	-	110	-	14	12	70
T6 <sup>c</sup>	≤ 5		290	-	250	-	8	6	95
	5 < $t$ ≤ 25		310	-	260	-	10	8	95
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	all		-	160	-	110	14	12	35
T4 <sup>c</sup>	≤ 25		205	-	110	-	14	12	70
Open profile T5	≤ 5		270	-	230	-	8	6	90
Open profile T6 <sup>c</sup>	≤ 5		290	-	250	-	8	6	95
	5 < $t$ ≤ 25		310	-	260	-	10	8	95
Hollow profile T5	≤ 5		270	-	230	-	8	6	90
Hollow profile T6 <sup>c</sup>	≤ 5		290	-	250	-	8	6	95
	5 < $t$ ≤ 25		310	-	260	-	10	8	95

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> Properties may be obtained by press quenching.  
<sup>d</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.

Table 48 — Alloy EN AW-6182 [Al Si1MgZr]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T4 <sup>c</sup>	≤ 220	≤ 155	205	-	110	-	12	10	-
T6 <sup>c, d</sup>	9 < $D$ ≤ 100	9 < $S$ ≤ 100	360	-	330	-	9	7	-
	100 < $D$ ≤ 150	100 < $S$ ≤ 150	330	-	300	-	8	6	-
	150 < $D$ ≤ 220	150 < $S$ ≤ 220	280	-	240	-	6	4	-
Extruded tube Not specified									
Extruded profile Not specified									
<p><sup>a</sup> <math>D</math> = Diameter for round bar.</p> <p><sup>b</sup> <math>S</math> = Width across flats for square and hexagonal bar, thickness for rectangular bar.</p> <p><sup>c</sup> Properties may be obtained by press quenching.</p> <p><sup>d</sup> Properties obtained by the user, however, may be lower than those listed if the material has been formed or otherwise cold or hot worked, particularly in the annealed temper, prior to normal solution heat treatment.</p>									

Table 49 — Alloy EN AW-7003 [Al Zn6Mg0,8Zr]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T5	all	all	310	-	260	-	10	8	-
T6 <sup>c</sup>	$\leq 50$	$\leq 50$	350	-	290	-	10	8	110
	$50 < D \leq 150$	$50 < S \leq 150$	340	,	280	-	10	8	110
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T5	all		310	-	260	-	10	8	-
T6 <sup>c</sup>	$\leq 10$		350	-	290	-	10	8	110
	$10 < t \leq 25$		340	-	280	-	10	8	110
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T5	all		310	-	260	-	10	8	-
T6 <sup>c</sup>	$\leq 10$		350	-	290	-	10	8	110
	$10 < t \leq 25$		340	-	280	-	10	8	110
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching. <sup>d</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.									



Table 50 — Alloy EN AW-7005 [Al Zn4,5Mg1,5Mn]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 50	≤ 50	350	-	290	-	10	8	110
	50 < $D$ ≤ 200	50 < $S$ ≤ 200	340	-	270	-	10	-	110
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 15		350	-	290	-	10	8	110
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 40		350	-	290	-	10	8	110
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 51 — Alloy EN AW-7108 [Al Zn5Mg1Zr]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.			
T6 <sup>c</sup>	≤ 100	≤ 100	310	-	260		10	8	90
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
T6 <sup>c</sup>	≤ 20	310	-	260	-	10	8	90	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ % min.	$A_{50\text{ mm}}$ % min.	$HBW$ Typical value	
		min.	max.	min.	max.				
T6 <sup>c</sup>	≤ 30	310	-	260	-	10	8	90	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 52 — Alloy EN AW-7108A [Al Zn5Mg1Zr(A)]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 200	≤ 200	310	-	260		12	10	90
T66 <sup>c</sup>	≤ 50	≤ 50	350	-	290	-	10	8	105
	50 < $D$ ≤ 200	50 < $D$ ≤ 200	340	-	275	-	10	-	105
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 20		310	-	260	-	12	10	90
T66 <sup>c</sup>	≤ 20		350	-	290	-	10	8	105
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 40		310	-	260	-	12	10	90
T66 <sup>c</sup>	≤ 40		350	-	290	-	10	8	105
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 53 — Alloy EN AW-7020 [Al Zn4,5Mg1]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 50	≤ 50	350	-	290	-	10	8	110
	50 < $D$ ≤ 200	50 < $S$ ≤ 200	340	-	275	-	10	-	110
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 15		350	-	290	-	10	8	110
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 40		350	-	290	-	10	8	110
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 54 — Alloy EN AW-7021 [Al Zn5,5Mg1,5]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6 <sup>c</sup>	≤ 40	≤ 40	410	-	350	-	10	8	120
Extruded tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T6 <sup>c</sup>	≤ 10	410	-	350	-	10	8	120	
Extruded profile									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
T6 <sup>c</sup>	≤ 20	410	-	350	-	10	8	120	
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 55 — Alloy EN AW-7022 [Al Zn5Mg3Cu]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 <sup>c</sup>	≤ 80	≤ 80	490	-	420	-	7	5	133
	80 < $D$ ≤ 200	80 < $S$ ≤ 200	470	-	400	-	7	-	
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 <sup>c</sup>	≤ 30		490	-	420	-	7	5	133
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511 <sup>c</sup>	≤ 30		490	-	420	-	7	5	133
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar. <sup>c</sup> Properties may be obtained by press quenching.									

Table 56 — Alloy EN AW-7049A [Al Zn8MgCu]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T6, T6510, T6511	$\leq 100$	$\leq 100$	610	-	530	-	5	4	170
	$100 < D \leq 125$	$100 < S \leq 125$	560	-	500	-	5	-	170
	$125 < D \leq 150$	$125 < S \leq 150$	520	-	430	-	5	-	170
	$150 < D \leq 180$	$150 < S \leq 180$	450	-	400	-	3	-	170
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511	$\leq 30$		610	-	530	-	5	4	170
Extruded profile									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511	$\leq 30$		610	-	530	-	5	4	170
<sup>a</sup> $D$ = Diameter for round bar. <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar.									

Table 57 — EN AW-7075 [Al Zn5,5MgCu]

Extruded rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	≤ 200	≤ 200	-	275	-	165	10	8	60
T6, T6510, T6511	≤ 25	≤ 25	540	-	480	-	7	5	150
	25 < $D$ ≤ 100	25 < $S$ ≤ 100	560	-	500	-	7	-	150
	100 < $D$ ≤ 150	100 < $S$ ≤ 150	530	-	470	-	6	-	150
	150 < $D$ ≤ 200	150 < $S$ ≤ 200	470	-	400	-	5	-	150
T73, T73510, T73511 <sup>c</sup>	≤ 25	≤ 25	485	-	420	-	7	5	135
	25 < $D$ ≤ 75	25 < $S$ ≤ 75	475	-	405	-	7	-	135
	75 < $D$ ≤ 100	75 < $S$ ≤ 100	470	-	390	-	6	-	135
	100 < $D$ ≤ 150	100 < $S$ ≤ 150	440	-	360	-	6	-	135
Extruded tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
O, H111	≤ 10		-	275	-	165	10	-	60
T6, T6510, T6511	≤ 5		540	-	485	-	8	6	150
	5 < $t$ ≤ 10		560	-	505	-	7	5	150
	10 < $t$ ≤ 50		560	-	495	-	6	4	150
T73, T73510, T73511 <sup>c</sup>	≤ 5		470	-	400	-	7	5	135
	5 < $t$ ≤ 25		485	-	420	-	8	6	135
	25 < $t$ ≤ 50		475	-	405	-	8	-	135
Extruded profile <sup>d</sup>									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T6, T6510, T6511	≤ 25		530	-	460	-	6	4	150
	25 < $t$ ≤ 60		540	-	470	-	6	-	150
T73, T73510, T73511 <sup>c</sup>	≤ 25		485	-	420	-	7	5	135

<sup>a</sup>  $D$  = Diameter for round bar.  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar.  
<sup>c</sup> For materials of thickness 20 mm or above, see EN 755-1, with respect to stress corrosion cracking resistance.  
<sup>d</sup> If a profile cross section is comprised of different thickness which fall in more than one set of specified mechanical property values, the lowest specified value shall be considered as valid for the whole profile cross section.



## Annex A (informative)

### List of tempers used in tables 1 to 57 (extract of EN 515)

Temper	Definition
F	as fabricated (no mechanical property limits specified)
O	annealed - products achieving the required annealed properties after hot forming processes may be designated as O temper
H111	annealed and slightly strain-hardened (less than H11) during subsequent operations such as stretching or straightening
H112	slightly strain-hardened from working at an elevated temperature or from a limited amount of cold work (mechanical property limits specified), such as stretching or straightening
T3	solution heat-treated, cold worked and naturally aged
T3510	solution heat-treated, stress-relieved by stretching a controlled amount (permanent set 1 % to 3 %) and naturally aged. The products receive no further straightening after stretching
T3511	same as T3510 except that minor straightening is allowed after stretching to comply with standard tolerances
T4	solution heat-treated and naturally aged
T4510	solution heat-treated, stress-relieved by stretching a controlled amount (permanent set 1 % to 3 %) and naturally aged. The products receive no further straightening after stretching
T4511	same as T4510 except that minor straightening is allowed after stretching to comply with standard tolerances
T5	cooled from an elevated temperature shaping process and then artificially aged
T6	solution heat-treated and then artificially aged
T64	solution heat-treated and then artificially aged in underageing conditions (between T6 and T61) to improve formability
T6510	solution heat-treated, stress-relieved by stretching a controlled amount (permanent set 1 % to 3 %) and then artificially aged. The products receive no further straightening after stretching
T6511	same as T6510 except that minor straightening is allowed after stretching to comply with standard tolerances
T66	solution heat-treated and then artificially aged - mechanical property level higher than T6 achieved through special control of the process (6000 series alloys)
T7	solution heat-treated and then artificially overaged
T73	solution heat-treated and then artificially overaged in order to achieve the best stress corrosion resistance
T73510	solution heat-treated, stress-relieved by stretching a controlled amount (permanent set 1 % to 3 %) and then artificially overaged in order to achieve the best stress corrosion resistance The products receive no further straightening after stretching
T73511	same as T73510 except that minor straightening is allowed after stretching to comply with standard tolerances
T8	solution heat-treated, cold worked and then artificially aged
T8510	solution heat-treated, stress-relieved by stretching a controlled amount (permanent set 1 % to 3 %) and then artificially aged. The products receive no further straightening after stretching
T8511	same as T8510 except that minor straightening is allowed after stretching to comply with standard tolerances

## **Bibliography**

- [1] EN 515, *Aluminium and aluminium alloys — Wrought products — Temper designations*
- [2] EN 573-3, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 3: Chemical composition*

Blank page with faint vertical text on the left edge.